



Poly-Shell™ 7000

LOW ODOR / LOW VOC

PRODUCT DESCRIPTION

SEAL-KRETE® Poly-Shell™ 7000 utilizes the latest development in Polyaspartic coating technology and is the most durable coating available. It dries quickly and provides unparalleled rapid return to service. It is extremely resistant to heat (temps up to 350°F), UV rays, and a variety of harsh chemicals, including salt, oil, and gasoline. Poly-Shell is also flexible and allows for natural concrete movement without cracking or peeling, making this system ideal for either indoor or outdoor applications.

FEATURES AND BENEFITS:

- VOC < 50, SCAQMD Approved, Low Odor
- Versatile – Coatings, Broadcast Floors, Chip Floors, Slurry/Broadcast
- Rapid Return to Service in 24 hours
- Outstanding Color and Gloss Retention
- Highly Chemical Resistant
- Available in:
 - Clear 2 Gallon Kit, Item # 243002
 - Clear 10 Gallon Kit, Item # 243005
 - 32 oz. Color Packs (see SEAL-KRETE High Performance Flooring Systems brochure for available colors)

RECOMMENDED USES:

- Restaurants
- Hospital and care facilities
- Manufacturing plants
- Universities
- Stadiums
- Residential garage floors, driveways, patios
- Kennels
- Veterinarian hospitals

Important: Read all directions thoroughly. Recommended: Wear gloves, safety glasses and protective clothing or apron.

SURFACE PREP*

New concrete should be allowed to cure for a minimum of 28 days. The concrete must be structurally sound, dry, and free of grease, oils, coatings, dust, curing compounds and other coatings or contaminants. Surface laitance must be removed. Rising moisture vapor emission rate must not exceed 3 lbs per 1000 sq. ft. over a 24 hour period as measured by calcium chloride test method ASTM F-1869. The preferred method of surface preparation is abrasive blasting or scarification using diamond heads to achieve a final 80–120 grit finish, reference Profile SP-2 ICRI Technical Guideline No. 03732. If patching is required, use SEAL-KRETE Fast Cure High Strength Concrete Repair.

ADDING COLORANT

Add colorant to Part A prior to mixing Parts A and B. Carefully monitor amount of colorant added to each gallon to ensure color is uniform. On large projects, make sure all colorant is from the same lot # or intermix all colorants.

AMOUNT OF COLORANT ADDED PER ONE GALLON OF PART A:

Opaque	16 oz*
Translucent	8 oz

*Do not add more than 16 ounces of colorant to a gallon of Part A for any reason.

APPLICATION

MIXING INSTRUCTIONS: Combine one part by volume of Part A with one part by volume of Part B and thoroughly mix using a low speed drill with mixing attachment for 3 minutes. Mix only what you can squeegee and backroll within 20-25 minutes (approximately 1 gallon of mixed material per crew of two applicators wearing spiked shoes). Do not aerate the mix.

SEAL-KRETE Poly-Shell 7000 can be applied using a notched squeegee or short nap lint-free mohair roller.

Refer to Application Guide or visit hp.seal-krete.com. for detailed application instructions.

CLEAN-UP, STORAGE AND DISPOSAL

CLEAN-UP: Clean tools and application equipment immediately after use with an active solvent like xylene (in SCAQMD use acetone only). Clean spills or drips while still wet with solvent. Dried SEAL-KRETE High Performance Poly-Shell will require mechanical abrasion for removal. Do not use alcohol "IPA" or Lacquer thinner blends that contain alcohol to clean equipment or tools.

HANDLING: Do not breathe mixed product vapors or dusts. Use adequate ventilation to keep airborne isocyanate levels below the exposure limits. Individuals with lung or breathing problems or prior allergic reactions to isocyanates must not be exposed to vapors or dusts.

KEEP FROM FREEZING: Store in a cool, well ventilated area above freezing.

DISPOSAL: Collect with absorbent material. Dispose of in accordance with current local, state and federal regulations.

LIMITATIONS

Do not aerate during mixing. Apply when temperature is -20° to 130°F. Do not apply if water or ice is present. Lower temperatures will slow cure time. Do not store SEAL-KRETE Poly-Shell at temperatures below 40°F. Cure new concrete 28 days before application. Do not apply to slabs on grade unless a heavy uninterrupted vapor barrier has been installed under the slab. Do not apply SEAL-KRETE Poly-Shell if the floor Moisture Vapor Rating is higher than 3 lbs. per 1000 sq. ft.

MAINTENANCE AND CARE

SEAL-KRETE Industrial Flooring Systems are monolithic, making them easier to clean because dirt and contaminants remain on the surface. For maintenance / care recommendations, refer to application guide or visit hp.seal-krete.com.

CAUTION: KEEP OUT OF REACH OF CHILDREN. Avoid contact with skin. If splashed in the eyes remove contact lenses if worn. Flush eyes with clean water. If irritation occurs get medical attention. If swallowed, DO NOT induce vomiting. Take immediately to hospital or physician. **For more information refer to Material Safety Data Sheet.**

*Sanding or removing paint containing lead may be hazardous. For information contact the National Lead Information Center at 1-800-424-LEAD or www.epa.gov/lead.



Poly-Shell™ 7000

MATERIAL PROPERTIES AT 75°F

Mixed VOC Content	< 50 g/L*
Mix Ratio (by volume)	1:1
Tack Free Time	2 hours
Recoat Time (min/max)	2 hrs / 24 hrs
Light Foot Traffic	6 hours
Vehicular Traffic (hours)	24 hours
ASTM D-570 – Water Absorption (24 hrs.)	< 0.5%
ASTM D-635 – Flammability	Self-extinguishing
ASTM D-638 – Tensile Strength psi	4,500–5,200 psi
ASTM D-638 – Tensile Elongation %	25%–30%
ASTM D-695 – Compressive Strength:	
@ 24 hours	6,700
@ 7 days	7,950
ASTM C-722 – Monolithic Surfacing	Pass
ASTM D-2794 – Impact Resistance	Pass
ASTM D-4060 – Abrasion Resistance (CS-17)	3 mg
ASTM D-4366 – König Hardness	137
ASTM D-4541 – Adhesion Strength	725 psi
*EPA Method 24 – Floor Category	

CHEMICAL RESISTANCE

Acetic Acid	Y	Methylene Chloride	Y
Acetone	Y	Mineral Spirits	Y
Ammonia 30%	Y	Motor Oil	Y
Ammonium Hydroxide 30%	Y	Mustard	Y
Animal Urine	Y	Nitric Acid 20%	Y
Antifreeze	Y	Nitric Acid 40%	Y
Benzyl Alcohol	Y	Orange Juice	Y
Brake Fluid	Y	Phosphoric Acid 10%	Y
Calcium Hypochlorite (Chlorine)	Y	Phosphoric Acid 30%	Y
Chromic Acid 10%	Y	Phosphoric Acid 50%	Y
Citric Acid 10%	Y	PM Solvent	Y
Clorox	Y	Silver Nitrate 20%	Y
Ethyl Acetate	Y	Skydrol	Y
Gasoline	Y	Sodium Hydroxide 50% (Caustic Soda)	Y
Glycol Ether	Y	Sodium Hypochlorite 15% (Bleach)	Y
Hydraulic Fluids	Y	Sodium Hypochlorite 50% (Bleach)	Y
Hydrochloric Acid 35%	Y	Sulfuric Acid 10% (Battery Acid)	Y
Hydrofluoric Acid 40%	S	Sulfuric Acid 50% (Battery Acid)	S
Hydrogen Peroxide 30%	Y	Tolulene	Y
Iodine 2%	Y	Trichloroethylene (1,1,1)	Y
MEK	Y	Trichloroethylene	Y
Methanol	Y	Windshield Wiper Fluid	Y
Methyl Cellosolve	Y	Xylene	Y

Key: Y = RESISTANT S = SPLASH & SPILL N = NOT RECOMMENDED

APPLICATION AND COVERAGE GUIDE

Steps	System Type					Coverage		
	Solid Color	Sparse Flake	Double Flake	Single Quartz	Double Quartz	Squeegee Size	Sq. Ft./ Gal	Mils
Primer Coat Clear or Tinted	√ Tinted	√ Tinted	√ Clear	√ Tinted	√ Clear	1/8"	150	10.7
Layer 1 Clear or Tinted	√ Tinted	√ Tinted	√ Clear	√ Tinted	√ Clear	1/8"	150	10.7
Broadcast (lbs./sq ft)	—	Vinyl Chip 0.05	Vinyl Chip 0.15	Quartz .50	Quartz .50	—	—	—
Layer 2 Clear	—	—	√	—	√	1/8"	150	10.7
Broadcast (lbs./sq ft)	—	—	Vinyl Chip 0.15	—	Quartz .50	—	—	—
Grout Coat Clear	—	√	√	√	√	1/8"*	150	10.7
Seal Coat Clear	√	√	√	√	√	flat*	200	8.0

Coverage rates are approximate and for estimating purposes only. Surface temperature, porosity, texture and thickness will determine actual material requirements.

*A larger notched squeegee can be used for a smoother surface.

WARRANTY: Seller makes no warranty, either expressed or implied, concerning this product, its quality, performance, merchantability, or fitness for a particular purpose other than expressly designated warranty of this label. Buyer assumes all risk of use and handling of this material.

TECHNICAL SUPPORT: For more information on surface prep or application guidelines, or to obtain a Material Safety Data Sheet, call 1-800-323-7357, M-F (8:00 am–5:00 pm EST) or visit our website at hp.seal-krete.com.

Country of Origin: U.S.A.



Convenience Products
306 Gandy Rd., Auburndale, FL 33823 USA
Questions or comments? e-mail: tech@seal-krete.com or call 1-800-323-7357

HOW TO TREAT CONCRETE™

hp.seal-krete.com