



SEAL KRETE® HIGH PERFORMANCE SURFACE-SHELL™ COVE BASE

DESCRIPTION AND USES

SEAL-KRETE® Surface-Shell™ Cove Base is a trowel-applied, chemical resistant and antimicrobial treated cementitious urethane cove mortar. Surface-Shell Cove Base is supplied with Polygiene® anti-microbial additive.

The Surface-Shell Cove Base product is typically installed by factory trained contractors. Be sure you are fully aware of all application procedures and have all the required equipment available prior to beginning the installation of this product.

FEATURES AND BENEFITS

- VOC <10 g/l, SCAQMD Approved
- Contains a silver ion antimicrobial additive to protect the surface
- Rapid Return to Service in 24 hours
- Low odor and non-toxic
- This coating complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities

PRODUCT

DESCRIPTION	SKU
Surface-Shell Cove Base 33 LF. Kit	SK571000

Kit Contents:

Part A - Base (.30 Gal.), Part B - Hardener (.25 Gal.) and Part C - Filler (26 Pounds)

COMPANION PRODUCTS

DESCRIPTION (Pigment Pack)	SKU
Surface-Shell Dark Grey	SK570003
Surface-Shell Grey	SK570006
Surface-Shell Green	SK570007
Surface-Shell Red	SK570008
Surface-Shell Cream	SK570010
Surface-Shell Custom	SK570099

NOTE: Pigment Pack sold separately.

RECOMMENDED TOPCOATS

- SealKrete HP Poly-Shell 7000
- SealKrete HP Poly-Shell 8000
- SealKrete HP Epoxy-Shell 1000 EPL

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

NEW CONCRETE: New concrete should be allowed to cure for a minimum of 28 days. The concrete must be structurally sound, dry, and free of grease, oils, dust, curing compounds and other coatings or contaminants. Surface laitance must be removed. Rising moisture vapor emission rate must not exceed 3 lb. per 1000 sq. ft. over a 24 hour period as measured by calcium chloride test method ASTM F-1869. The preferred method of surface preparation is to mechanically abrade the floor by diamond grinding to achieve a final 60-80 grit finish, reference profile CSP-5 according to ICRI. If patching is required, use SEAL-KRETE Fast Cure High Strength Concrete Repair

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding or sweep blasting to create a surface profile. The Surface-Shell Cove Base is compatible with most coatings, but a test patch is suggested.

NOTE: Concrete should have a minimum of 3,000 psi compressive strength. Concrete must be visibly dry at time of application. Anchor grooves, minimum 4mm wide x 4mm deep, must be formed at all edges, bay joints, columns, doorways, and drains across the floor.

MIXING EQUIPMENT

Low speed drill and 3" Jiffler Mixer or Hanson Plunge Mixer.

Important: Hand mixing will produce inconsistent results and is not an approved method.

MIXING

Thoroughly mix each component separately before combining. Pour the base (Part A) and hardener (Part B) components together in a clean, dry 5-gallon (18.93 L) container and power mix using a 3" (7.6 cm) Jiffler Mixer or Hanson Plunge Mixer. While mixing, slowly add filler (Part C) and Pigment Pack (Part D) and continue to mix until uniform color is achieved.

DO NOT THIN



SEAL KRETE® HIGH PERFORMANCE SURFACE-SHELL™ COVE BASE

PRODUCT APPLICATION (cont.)

APPLICATION EQUIPMENT

Steel hand trowel

APPLICATION

Apply a tack coat of the reserved resin left in the bucket after combining part A and B into the 5 gallon pail, ensuring enough resin is left to apply the thin tack coat primer. Apply the Surface-Shell Cove Base using a steel trowel, slightly thicker than the thickness required. Compact and finish to the required thickness using a steel-coving trowel. Normally the vertical edge is formed first, then the horizontal and finally the cove radius.

CLEAN UP

Applicators and equipment should be cleaned immediately after use with an active solvent like xylene (in SCAQMD, use acetone only). Clean spills or drips while still wet with solvent. Dried Surface-Shell Cove Base will require mechanical abrasion for removal.

PERFORMANCE CHARACTERISTICS

COMPRESSIVE STRENGTH

METHOD: ASTM C579
 RESULT: 8,000 psi (55 MPa)

TENSILE STRENGTH

METHOD: ASTM C307
 RESULT: 1,450 psi (10 MPa)

BOND STRENGTH TO CONCRETE

METHOD: ASTM D4541
 RESULT: Minimum 400 psi (100% concrete failure)

FLEXURAL STRENGTH

METHOD: ASTM C580
 RESULT: 2,900 psi (20 MPa)

ABRASION RESISTANCE

METHOD: ASTM D4060 (CS 17 wheels, 1000 cycles)
 RESULT: 079 g weight loss

COEFFICIENT OF THERMAL EXPANSION

METHOD: ASTM C531
 RESULT: 1.1x10⁻⁵ in/in/F°

COEFFICIENT FRICTION

METHOD: ASTM D2047
 RESULT: Exceeds ADA recommendations

TEMPERATURE RESISTANCE

METHOD: Continuous exposure
 RESULT: 220°F

METHOD: Intermittent spills
 RESULT: 250°F



SEAL KRETE® HIGH PERFORMANCE SURFACE-SHELL™ COVE BASE

PHYSICAL PROPERTIES

		SURFACE-SHELL COVE BASE
Resin Type		Cementitious Urethane
Pigment Type		Varies depending on color
Weight	Per Gallon	8.4-10.2 lbs.
	Per Liter	1.0-1.2 kg
Solids	By Weight	100%
	By Volume	100%
Volatile Organic Compounds		<10 g/l
Recommended Dry Film Thickness (DFT) Per Coat		250 mils
Practical Coverage		33 linear ft./per kit at 4" high at 3/16"
Mixing Ratio		1 Part A : 1 Part B : 1 Part Filler (only complete kits should be used)
Pot Life @ 77°F (25°C) and 50% Relative Humidity		20-25 minutes
Re-Coat Window (Min./Max)		12 hours/24 hours
Dry Times at 77°F (25°C) and 50% Relative Humidity	Foot Traffic	6-8 hours
	Vehicle Traffic	12-16 hours
	Full Cure*	3-5 days
Dry Heat Resistance		250°F (121°C)
Shelf Life		2 years
Flash Point		>350°F (>176°C)
Safety Information		For additional information, see SDS

*Coating achieves its full physical and chemical resistant properties.
 Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.