



**SEAL KRETE® HIGH PERFORMANCE
FAST CURE - RAPID REPAIR**

DESCRIPTION AND USES

SEAL-KRETE® High Performance Fast Cure - Rapid Repair is a two component, 100% solids polyurea crack repair compound. This ultra fast cure crack repair can be used at temperatures as low as -5°F (-20.5°C) and is suitable for traffic in 15 minutes.

PRODUCT FEATURES

- Bonds well to a variety of substrates including concrete, wood, fiberglass and asphalt
- Fast cure times, even in cold temperatures
- Return to service in 10-30 minutes
- Virtually no odor

PRODUCT

DESCRIPTION (Kit)	SKU
Gray	347355

PACKAGING

1 gallon kit containing both components Part A and Part B components are packaged in 1/2 gallon plastic containers. Kit yields one full gallon.

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

New concrete must cure 30 days at 70°F (21°C) before repairs are made. Remove all dirt, grease, oil, salt or other contaminants by washing surface with Krud Kutter® Original Cleaner Degreaser, commercial detergent or other suitable cleaner. Rinse thoroughly with fresh, clean water. Remove all loose, unsound, or deteriorated concrete.

Small hairline cracks must be chased using a v-shaped diamond crack chasing blade on a hand held grinder. The crack should be opened to a minimum of ¼ inch wide. Any oil or grease that may have seeped into a crack and contaminated the edge of the concrete must be removed by grinding if washing is not sufficient. Use dry silica sand to fill deep cracks leaving a depth of ¼ inch down from the surface. The Fast Cure - Rapid Repair will soak into the silica and fortify the patch.

PRODUCT APPLICATION (cont.)

MIXING

Mix both components separately prior to combining. Pour out equal volumes of each component, then combine and mix together for 20-30 seconds. Fast Cure - Rapid Repair cures very quickly, so only mix up amounts that can be used within 5 minutes. Once mixed, Fast Cure - Rapid Repair is an easy flowing liquid. For some repairs, such as spalled areas or edge repair, dry silica sand can be added and mixed in to create a trowelable paste. Never use more than one part silica to one part activated liquid.

APPLICATION

Fast Cure - Rapid Repair is suitable for application temperature down to -5°F (-20.5°C). Within one minute of mixing, pour Fast Cure - Rapid Repair into the crack to be filled. Fill the crack to a slight excess and allow to cure. Fast Cure - Rapid Repair will cure in 10-15 minutes. Once cured, and the material cannot be indented by a thumbnail, the excess material can be removed by grinding to a flush surface.

NOTE: Fast Cure - Rapid Repair must be profiled by grinding or sanding if it is going to be topcoated.

THINNING

None required

CLEAN-UP

Methyl Ethyl Ketone (MEK).

PERFORMANCE CHARACTERISTICS

TENSILE STRENGTH

METHOD: ASTM D412
RESULT: 4,800

ABRASION RESISTANCE

METHOD: ASTM D4060, CS 17 Wheel, 1,000 g load, 1,000 cycles
RESULT: 20 mg loss

HARDNESS, DUROMETER

METHOD: ASTM D2240
RESULT: 67-72 D

COMPRESSIVE STRENGTH

METHOD: ASTM C109
RESULT: 5,600 and with silica added 6,200

ELONGATION

METHOD: ASTM D412
RESULT: 6-8%

TECHNICAL DATA**SKHP-10**

SEAL KRETE® HIGH PERFORMANCE FAST CURE - RAPID REPAIR

PHYSICAL PROPERTIES

		FAST CURE - RAPID REPAIR
Resin Type		Polyurea
Solids	By Weight	100%
	By Volume	100%
Mixing Ratio		1 (base) : 1 (activator) by volume
Induction Period		None
Working Time		5 minutes @ 77°F (25°C)
Pot Life		None. Pour out all material immediately after mixing
Estimated Coverage*		230 linear feet per activated gallon @ 1/4" wide and 1/4" deep
Dry Times at 72°F (22°C) and 50% Relative Humidity	Dry Hard	5-10 minutes
	Foot Traffic	10 minutes
	Vehicle Traffic	30 minutes
Shelf Life		5 years
Safety Information		See SDS

*Coverage rate is estimated and accounts for material lost when grinding away excess material for a smooth finish.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 800-323-7357
www.hp.seal-krete.com

Form: ARJ-1861
Rev.: 041020