



**SEAL KRETE® HIGH PERFORMANCE  
POLY-SHELL™ 7000**

**DESCRIPTION AND USES**

SEAL-KRETE® Poly-Shell™ 7000 utilizes the latest development in Polyaspartic coating technology and is the most durable coating available. It dries quickly and provides unparalleled rapid return to service. It is extremely resistant to heat (temps up to 350°F), UV rays, and a variety of harsh chemicals, including salt, oil, and gasoline. Poly-Shell 7000 is also flexible and allows for natural concrete movement without cracking or peeling, making this system ideal for either indoor or outdoor applications.

**PRODUCT FEATURES AND BENEFITS**

- VOC < 50 g/l, SCAQMD Approved
- Versatile – Coatings, Broadcast Floors, Chip Floors, Slurry/Broadcast
- Rapid Return to Service in 24 hours
- Outstanding Color retention in Gloss or Satin Finish
- Highly Chemical Resistant (for more information, see chart on page 2)
- Convenient 1:1 mixing ratio
- Designed for interior and exterior applications

**PRODUCTS**

DESCRIPTION (Clear)	2 Gallons
Polly-Shell 7000 Gloss Kit	SK243002
Polly-Shell 7000 Satin Kit	SK244002

**PRODUCT APPLICATION**

**READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT**

**SURFACE PREPARATION**

**NEW CONCRETE:** New concrete should be allowed to cure for a minimum of 28 days. The concrete must be structurally sound, dry, and free of grease, oils, dust, curing compounds and other coatings or contaminants. Surface laitance must be removed. Rising moisture vapor emission rate must not exceed 3 lb. per 1000 sq. ft. over a 24 hour period as measured by calcium chloride test method ASTM F-1869. The preferred method of surface preparation is to mechanically abrade the floor by diamond grinding to achieve a final 80–120 grit finish, reference profile CSP-2 according to ICRI. If patching is required, use SEAL-KRETE Fast Cure High Strength Concrete Repair.

**PREVIOUSLY COATED:** Previously coated concrete must be in good sound condition with the existing coating tightly adhering to the concrete. In addition to the aforementioned cleaning the existing coating must be abraded to dull the finish and produce a slight surface profile. Remove all sanding dust by vacuum. The Poly-Shell 7000 is compatible with most coatings, but a test patch is suggested. Concrete must be visibly dry at time of application.

**PRODUCT APPLICATION (cont.)**

**MIXING EQUIPMENT**

Low speed drill and spiral mixing wand.

Important: Hand mixing will produce inconsistent results and is not an approved method.

**MIXING**

Note: Before starting, ensure that the material, concrete surface, and the ambient air are all at 30-90°F. Mixing ratio is 1 part A to 1 part B.

Pre-mix both A and B sides prior to combining.

Add part “A” to the mixing container.

Add part “B” to the mixing container and mix for 60-90 seconds.

**DO NOT THIN**

**TINTING**

Add 16 ounces (1/2 can) of Poly-Shell color pack to activated 2 gallon kit (Parts A and B) and stir for 3 minutes. Carefully monitor amount of colorant added to each gallon to ensure color is uniform. On large projects, make sure all colorant is from the same lot # or intermix all colorants. Tint is to be added in the field at the time of application.

**APPLICATION EQUIPMENT**

- 24” flat blade squeegee
- 18”-3/8” lint free roller

**APPLICATION**

Mix only what you can squeegee and back roll within 35-40 minutes (approximately 1 gallon of mixed material per crew of two applicators wearing spiked shoes). Do not aerate the mix.

Before starting, ensure that the material, concrete surface, and the ambient air are all at 30-90°F. Do not apply in direct sunlight or when temperature is rising. Colder environmental conditions can slow the cure of Poly-Shell 7000. For application outside of this temperature range please contact Rust-Oleum Technical Service. Wearing spiked shoes, immediately pour mixed Poly-Shell 7000 on the floor in ribbons. Spread using a squeegee and then back roll using a short nap lint-free roller.

**CLEAN UP**

Clean Tools and application equipment immediately after use with active solvent like xylene (in SCAQMD use acetone only). Clean spills or drips while still wet with solvent. Dried product will require mechanical abrasion for removal.



**SEAL KRETE® HIGH PERFORMANCE  
POLY-SHELL™ 7000**

**CHEMICAL RESISTANCE**

CHEMICAL	RESULT (77°F/25°C)
Acetic Acid 100%	C
Acetone	C
Ammonium Hydroxide 50%	RC
Benzene	C
Brine saturated H2O	R
Chlorinated H2O	R
Clorox(10%) H2O	R
Diesel fuel	RC
Gasoline	RC
Gasoline/5% MTBE	RC
Gasoline/5% Methanol	RC
Hydrochloric Acid 20%	R
Hydrofluoric Acid 10%	NR
Hydraulic fluid (oil)	RC
Isopropyl Alcohol	R
Lactic Acid	RC
MEK	RC
Methanol	R
Methylene Chloride	C
Mineral Spirits	RC
Motor Oil	R
MTBE	C
Muriatic Acid 10%	R
NaCl/H2O 10%	R
Nitric Acid 20%	NR
Phosphoric Acid 10%	R
Phosphoric Acid 50%	NR
Potassium Hydroxide 10%	R
Potassium Hydroxide 20%	R, Dis
Propylene Carbonate	RC
Skydrol	C
Sodium Hydroxide 25%	R
Sodium Hydroxide 50%	R, Dis
Sodium Hypchlorite 10%	R
Sodium Bicarbonate	R
Stearic Acid	R
Sugar/H2O	R
Sulfuric Acid 10%	R
Sulfuric Acid >50%	RC
Toluene	R
1, 1,1-Trichlorethane	C
Trisodium Phosphate	R
Vinegar/H2O 5%	R
Xylene	RC

**Chemical Resistance: Chart Key**

R=recommended/little or no visible damage  
 RC=recommended conditional/some effect, swelling or discoloration  
 C=Conditional/Cracking-wash within one hour of spillage to avoid affects  
 NR=Not recommended  
 Dis=discolorative

**PERFORMANCE CHARACTERISTICS**

**COMPRESSIVE STRENGTH**

METHOD: ASTM C695  
 RESULT: @ 24 hours 6,700 psi  
 @ 7 days 7,950 psi

**TENSILE STRENGTH**

METHOD: ASTM D638  
 RESULT: 4500-5200 psi

**BOND STRENGTH TO CONCRETE**

METHOD: ASTM D4541  
 RESULT: 725 psi

**TABER ABRASION**

METHOD: ASTM 4060, CS 17  
 RESULT: 3 mg.

**FLAMMABILITY**

METHOD: ASTM D635  
 RESULT: Self-extinguishing

**KONIG HARDNESS**

METHOD: ASTM D4366  
 RESULT: 137

**ELONGATION**

METHOD: ASTM D638  
 RESULT: 25-35%

**WATER ABSORPTION**

METHOD: ASTM D570  
 RESULT: (24 hours) <0.5%

**MONOLITHIC SURFACING**

METHOD: ASTM C722  
 RESULT: Pass

**IMPACT RESISTANCE**

METHOD: ASTM D2794  
 RESULT: Pass

This product complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized. Meets USDA requirements for incidental food contact.



**SEAL KRETE® HIGH PERFORMANCE  
POLY-SHELL™ 7000**

**PHYSICAL PROPERTIES**

		<b>POLY-SHELL 7000</b>
<b>Resin Type</b>		Polyaspartic Polyurea
<b>Pigment Type</b>		Varies depending on color
<b>Solvents</b>		Benzyl Alcohol
<b>Weight*</b>	<b>Per Gallon</b>	9.59 lbs.
	<b>Per Liter</b>	1.1 kg
<b>Solids*</b>	<b>By Weight</b>	70%
	<b>By Volume</b>	70%
<b>Volatile Organic Compounds*</b>		<50 g/l
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		4-8 mils
<b>Practical Coverage (assume 15% material loss)</b>		120-240 sq.ft./gal. Coverage rates will vary based on application method.
<b>Mixing Ratio</b>		1:1
<b>Pot Life @ 70-80°F (21-27°C) and 50% Relative Humidity</b>		35-40 minutes
<b>Re-Coat Window (Min./Max)</b>		2 hours/12 hours
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Foot Traffic</b>	2-4 hours
	<b>Vehicle Traffic</b>	24 hours
	<b>Full Cure**</b>	7 days
<b>Shelf Life</b>		5 years
<b>Flash Point</b>		>200°F (93°C)
<b>WARNING!</b>	<b>CAUSES NOSE, THROAT, EYE AND SKIN IRRITATION. CAUSES EYE AND SKIN BURNS. HARMFUL IF SWALLOWED. MAY CAUSE ASTHMA, SKIN SENSITIZATION OR OTHER ALLERGIC RESPONSES. FOR INDUSTRIAL OR COMMERCIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN. SEE THE PRODUCT SAFETY DATA SHEET (SDS) AND LABEL WARNINGS FOR ADDITIONAL SAFETY INFORMATION.</b>	
<b>Safety Information</b>		For additional information, see SDS

\* Activated material

\*\*Coating achieves its full physical and chemical resistant properties.

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.